

Product Data Sheet

Product Name *3-D Life* Dextran-PEG Hydrogel SG

Catalog Number G92-1

Description The *3-D Life* Dextran-PEG Hydrogel SG Kit provides reagents for setting up slow gelling, cell-compatible hydrogels. Its major components are SG-Dextran and the crosslinker PEG-Link. When the two reagents are combined, thiol groups on PEG-Link form stable thioether bonds with thiol-reactive groups on SG-Dextran, which results in the formation of the gel. The components are mixed at physiological pH (pH 7.2) for optimal cell compatibility. The slow gelation kinetics allows enough time to conveniently manipulate the solution before the onset of gel formation.





Prior to the crosslinking step, cell adhesion peptides (e.g. *3-D Life* RGD Peptide, Cat. No. 09-P-001) can be covalently attached to a portion of the SH-reactive groups on SG-Dextran to provide a cell-adhesive matrix.

Dextran hydrogels can be dissolved by the addition of dextranase (*3-D Life* Dextranase, Cat. No. D10-1), which allows the recovery of chemically fixed or live cells for post-culture analyses (e.g. RT-PCR) or for further cultivation.

For more information and instructions, please consult the General Protocol GP-2 "Preparation of *3-D Life* Slow Gelling Hydrogels" and the *3-D Life* Hydrogels User Guide on www.cellendes.com.

Quantity Allows formation of up to 2 ml *3-D Life* Hydrogel depending on the stiffness of the gel.

Components

Material	Quantity	Concentration of reactive groups	Storage
 SG-Dextran	170 µl	30 mmol/L	Short term (≤2 months): 4°C Long Term: -80°C
 PEG-Link, lyophilized	200 µl*	20 mmol/L*	Lyophilisate and after reconstitution: -20°C to -80°C
 10x CB (pH 7.2)	200 µl	n.a.	Short term (≤2 months): 4°C Long term: -20°C or lower
 Water	2x 1500 µl	n.a	Room temperature or lower

All materials are filter-sterilized.

*Volume/concentration after reconstitution of lyophilisate.

Continued on next page.

Reconstitution PEG-Link:

1. Briefly centrifuge vial containing the PEG-Link lyophilisate to make sure that the entire material is at the bottom of the reaction tube.
2. Add 188 µl *3-D Life* Water per tube for a concentration of 20 mmol/L thiol groups. This results in a 200 µl PEG-Link solution.
3. Close tube and briefly vortex.
4. Incubate for 5 min.
5. Briefly vortex and centrifuge again.
6. PEG-Link is now ready for use.

Intended for research use only. Not for use in human therapeutic or diagnostic applications.